



Consumer and  
Corporate Affairs Canada

Consommation  
et Corporations Canada

(11) (A) No. 1 248 292

(45) ISSUED 890103

(52) CLASS 402-534  
C.R. CL. 402-528

(51) INT. CL. C08F 214/24,6/00<sup>4</sup>

(19) (CA) **CANADIAN PATENT** (12)

(54) Melt-Processible Tetrafluoroethylene Copolymers and  
Processes for Preparing Them

(72) Buckmaster, Marlin D.;  
Foss, Ray V.;  
Morgan, Richard A.,  
U.S.A.

(73) Granted to du Pont (E.I.) de Nemours and Company  
U.S.A.

(21) APPLICATION No. 480,923

(22) FILED 850507

(30) PRIORITY DATE U.S.A. (608,862) 840510

NO. OF CLAIMS 14 - NO DRAWING

Canada

DISTRIBUTED BY THE PATENT OFFICE OTTAWA  
CCA 274 (11/82)

TITLE

5 Melt-Processible Tetrafluoroethylene  
Copolymers and Processes for Preparing Them

FIELD OF THE INVENTION

10 This invention relates to melt-processible  
tetrafluoroethylene copolymers having good particle  
flow characteristics and thermal stability.

Such melt-processible copolymers can be  
extruded onto wire or extruded into film or tubing,  
or used as a coating, or can be used in rotomolding  
applications to make hollow articles or linings.

BACKGROUND OF THE INVENTION

15 Tetrafluoroethylene polymers are of two  
types. One is non-melt-processible polymers where  
the melt viscosity is too high to process the  
polymers by ordinary melt-extrusion processes.  
20 Instead, the polymers are ordinarily sintered or  
paste extruded depending on the type polymer made.  
The other class is melt-processible  
tetrafluoroethylene copolymers having melt  
viscosities in the melt extrudable range.

25 Melt-processible tetrafluoroethylene (TFE)  
copolymer resins directly from the polymerizer and/or  
coagulator are referred to as fluff or powder. The  
fluff is normally humid heat treated and/or melt  
extruded to stabilize it, such as described in U.S.  
30 Patent 3,085,083. There are applications such as  
rotocasting in which a free-flowing powder (herein  
called "granules") is preferable to melt-extruded  
pellets or where a high degree of purity of the resin  
is desired. Although rotolining and rotocoating  
AD 5415 35 processes differ in several technical respects from  
rotomolding, for the sake of convenience the term  
"rotocasting" is used herein to refer to all three  
generically unless otherwise indicated.



To facilitate handling of such granules, it is desirable to improve particle characteristics. Melt-processible copolymers that are coagulated from an aqueous dispersion and dried are friable, and form fines easily which give poor handling properties. It would be desirable to provide a melt-processible copolymer that is both stable and easily handled in a minimum of processing steps. It is particularly desirable to provide a copolymer that could be used both in conventional melt-fabrication processes and in rotocasting applications where particle characteristics are important.

It is also desirable to obtain resins that are thermally stable. A number of stabilization approaches are known in the art, most of which require melting the resins. Thus resins stabilized by these methods are generally available only as pellets -- not (without tedious and expensive regrinding steps) as the free-flowing granules that are the basis of this invention.

Another desirable feature of such resins is that the granules should be low in metal contamination. If the granules have been melted in traditional thermoplastic processing equipment, contamination occurs inevitably when the corrosive tetrafluoroethylene copolymer melts come in contact with the interior metal surfaces of thermoplastic processing equipment, even when corrosion-resistant alloys are used. Copolymers having low levels of metal contamination are particularly desirable for applications in the semiconductor industry.

#### SUMMARY OF THE INVENTION

A conventional product form for melt-processible tetrafluoroethylene copolymers is extruded pellets -- either strand-cut right

5 cylinders, or melt-cut discs or cylinders. These pellets are used as the feed to thermoplastic processing equipment.

An alternative product form for melt-fabricable tetrafluoroethylene copolymers is very finely divided powders. This product form has  
10 been used as the feedstock for coating operations, which are well known in the trade.

The subject of this patent is a new product form, namely, free-flowing, attrition-resistant, generally spherical, heat-stable granules. These  
15 granules are of high purity and thermal stability in air, having particular utility in fabricating free-standing rotomolded articles and providing defect-free polymeric coatings or linings, especially those produced by rotolining metal process  
20 equipment. The novel compositions have improved thermal stability and low bubble tendency. More specifically, the composition is a melt-processible, substantially nonelastomeric tetrafluoroethylene copolymer comprising 80-99.5 mole %  
25 tetrafluoroethylene and 0.5 to 20 mole % of at least one copolymerizable comonomer, which copolymer has  
(a) a melt viscosity between  $0.1 \times 10^4$  and  $100 \times 10^4$  poise at  $372^\circ\text{C}$ ,  
(b) a substantially spherical particle  
30 shape and a sphere factor less than 1.5,  
(c) an attrition factor of less than 60,  
(d) fewer than a total of 80 unstable  
35 end groups per  $10^6$  carbon atoms, and

- 5 (e) an average particle size  
between 200 and 3000 micrometers.


The process of this invention starts with melt-processible tetrafluoroethylene copolymers that have been polymerized in an aqueous medium and contain unstable end groups. When prepared in an aqueous medium, the copolymers are isolated by solvent-aided coagulation preceded by gelation. The resulting coagulated granules are spherical in shape, which facilitates handling. The granules are then dried and hardened by subjecting them to elevated temperature between the differential scanning calorimeter (DSC) peak melting point and 25°C below the melt onset temperature (i.e., the granules are heat treated to harden them, but not so as to completely melt or substantially deform them). The hardening facilitates screen sieving or mechanical screen sifting into desired particle sizes and facilitates handling by reason of reduced friability. The granules are then subjected to an atmosphere containing fluorine to convert unstable end groups to stable fluorinated end groups, thereby reducing bubbling or evolution of volatiles during further end-use heat processing.

These granules are especially well suited for rotocasting applications because of the optimal particle size and free-flowing characteristics combined with low bubble tendency.

A further benefit of the stabilized free-flowing granules is that such granules have not been melted in conventional thermoplastic processing equipment and are low in metal contamination.

DESCRIPTION OF THE INVENTION

5 Representative fluorinated ethylenically unsaturated comonomers copolymerizable with tetrafluoroethylene are represented by the formulas:



wherein  $\text{R}_1$  is  $-\text{R}_f$ ,  $-\text{R}_f-\text{X}$ ,  $-\text{O}-\text{R}_f$  or  $-\text{O}-\text{R}_f-\text{X}$  in which  $\text{R}_f$  is a perfluoroalkyl radical of 1-12 carbon atoms,  $-\text{R}_f-$  is a perfluoroalkylene diradical of 1-12 carbon atoms in which the attaching valences are at each end of the chain, and  $\text{X}$  is  $\text{H}$  or  $\text{Cl}$ ; and  $\text{R}_2$  is  $-\text{R}_f$  or  $-\text{R}_f-\text{X}$ .

Specific copolymerizable fluorinated ethylenically unsaturated comonomers include hexafluoropropylene, perfluoro(methyl vinyl ether), perfluoro(n-propyl vinyl ether), perfluoro(n-heptyl vinyl ether), 3,3,3-trifluoropropylene-1, 3,3,4,4,5,5,6,6,6-nonafluorohexene-1, 3-hydroperfluoro(propyl vinyl ether), or mixtures thereof, such as a mixture of hexafluoropropylene and perfluoro(propyl vinyl ether). Preferably the comonomers are selected from perfluoro(alkyl vinyl ethers) of the formula  $\text{R}_f-\text{O}-\text{CF}=\text{CF}_2$ ; or hexafluoropropylene; or compounds of the formula  $\text{R}_f-\text{CH}=\text{CH}_2$ , wherein  $-\text{R}_f$  is a perfluoroalkyl group of 1-12 carbon atoms.

Comonomer content can range from 0.5 mole percent up to about 20 mole percent, and more than one comonomer can be present.

35

5       The comonomer content is low enough that the copolymers are plastics rather than elastomers, i.e., they are partially crystalline and after extrusion do not exhibit a rapid retraction to original length from a stretched condition of 2X at room temperature.

10       The aqueous polymerization of TFE with various comonomers is well known. The reaction medium consists of water, monomers, a dispersing agent, a free-radical polymerization initiator, optionally, a chain-transfer agent and, optionally, a water-immiscible fluorocarbon phase, as described, for example, in U.S. Patent 3,635,926.

15       Polymerization temperatures between 20°-140°C may be employed and pressures of 1.4-7.0 MPa are ordinarily used. Generally higher temperatures and pressures are employed to increase polymerization rates, especially if a comonomer is less reactive relative to TFE. The TFE and sometimes the comonomer are fed continuously to the reaction vessel to maintain reaction pressure, or in some instances the comonomer is all added initially and pressure is maintained with TFE feed only. The monomer(s) are fed until the desired final dispersion solids level (15-50%) is achieved. The agitator speed in the reaction vessel may be held constant during polymerization or it may be varied to control polymerization rate.

25       Initiators commonly employed are free-radical initiators such as ammonium or potassium persulfate or disuccinic acid peroxide. The dispersing agent will be present in an amount between 0.01-0.5 percent based on weight of aqueous medium and preferably between 0.05-0.1 percent.

By the term "melt-processible" is meant that the copolymer can be processed (i.e., fabricated into shaped articles such as films, fibers, tubes, wire coatings and the like) by conventional melt-processing equipment. Such requires that the melt-viscosity of the copolymer at the processing temperature be no more than  $10^7$  poise. Preferably it is in the range of  $10^4$  to  $10^6$  poise at  $372^\circ\text{C}$ .

Melt viscosities of the melt-processible polymers are measured according to American Society for Testing and Materials Method D-1238, modified as follows: The cylinder, orifice and piston tip are made of a corrosion-resistant alloy, such as Haynes Stellite(tm) 19 or Inconel(tm) 625. The 5.0 g sample is charged to the 9.53 mm inside diameter cylinder which is maintained at  $372^\circ\text{C} \pm 1^\circ\text{C}$ . Five minutes after the sample is charged to the cylinder, it is extruded through a 2.10 mm diameter, 8.00 mm long square-edge orifice under a load (piston plus weight) of 5000 grams. This corresponds to a shear stress of 44.8 kPa. The melt viscosity in poises is calculated as 53170 divided by the observed extrusion rate in grams per minute.

The copolymers prepared by the foregoing aqueous polymerization process are colloiddally dispersed in the polymerization medium. The polymer is recovered from the dispersion by coagulation. Normal coagulation of aqueous polymer dispersions by mechanical shear tends to give a very finely divided powder which has poor handling characteristics. Several techniques might be used to obtain the preferred larger particle sizes. The combination of mechanical agitation and certain chemical additions can be used to obtain larger, spherical particles.



5 In the process of the invention, the aqueous  
dispersion is gelled with a gelling agent, a mineral  
acid, while being agitated. Preferably nitric acid  
is used as the gelling agent. A water-immiscible  
liquid is then added to the gel while continuing the  
10 agitation. The gel breaks up into separate phases of  
water and liquid-wetted polymer particles. The  
particles are then dried. The granule size is a  
function of the dispersion particle size, the ratio  
of water-immiscible liquid to polymer, and the  
agitation conditions. The granule size is, as  
15 desired, much larger than that achieved if the  
dispersion is coagulated by mechanical shear action  
alone. Usually, the amount of water-immiscible  
liquid will be 0.25 to 1.0 part per part of polymer  
on a dry weight basis. About 0.1 to 10 parts of  
20  $\text{HNO}_3$  per 100 parts of polymer weight can be used.  
Nitric acid is preferred because it is not corrosive  
to stainless-steel equipment and readily volatilizes  
in a subsequent baking step. Coagulated particles  
obtained by this process generally have a size  
between 200-3000 micrometers. The product is  
25 separated, washed and dried at 80 to 150°C for from 4  
to 30 hours.

Preferably, the water-immiscible liquid  
should have a surface tension of not more than 35  
30 dyne/cm at 25°C and it should have a normal boiling  
point in the range of 30 to 150°C. Typical examples  
of the immiscible liquid usable in the invention are  
aliphatic hydrocarbons such as hexane, heptane,  
gasoline and kerosene, or mixtures thereof,

35

5 aromatic hydrocarbons such as benzene, toluene and  
xylene, halogenated derivatives such as carbon  
tetrachloride, monochlorobenzene, the  
trichlorotrifluoroethanes,  
difluorotetrachloroethanes, and liquid oligomers of  
chlorotrifluoroethylene.

10 Other techniques might also be used to  
obtain the particle sizes preferred in this  
invention. Nucleation agents might be added to the  
aqueous dispersion before coagulation which would  
result in larger particle sizes. Small polymer  
15 particles which were obtained from mechanical  
coagulation might be redispersed in a two-phase  
liquid mixture and thus agglomerated into larger  
particles. The polymerization itself might be  
carried out with a water/immiscible liquid mixture so  
20 that particles of the desired size could be obtained  
directly from polymerization.

The dried particles are generally spherical  
and have a sphere factor less than 1.5, and  
preferably less than 1.2. The sphere factor is a  
25 measure of the degree of roundness of the particles.  
A sphere factor of 1 represents a geometrically  
spherical particle.

The particles are then hardened by heat  
treatment until the attrition factor, as described  
30 herein, is less than 60 and preferably less than 25,  
but before the granules agglomerate.

35

-10-

By the term "before the granules agglomerate" is meant that the D50 as hereinafter defined does not increase by more than 20%.

Heat hardening of the granules formed in the coagulation step occurs relatively close to the copolymer melting point. The temperature at which hardening occurs depends not only on the copolymer melting point but also on other characteristics such as comonomer and molecular weight distributions. These characteristics influence the temperature at which the onset of melting occurs.

This heat-hardening phenomenon occurs when the copolymer granules are held at a temperature within the range between the copolymer melting point and a temperature 25°C below the melt onset temperature, as measured by differential scanning calorimetric (DSC) methods described herein. The granules must be exposed to temperatures within this range for a time sufficient to impart a useful degree of hardness. The resulting heat-hardened granules are not completely melted and are only partially sintered. If the melting heat ratio as hereinafter defined is below 1.2, the polymer granules have been melted and begin to fuse together. After heat hardening, the granules have a level of hardness useful in preventing attrition and fines generation during subsequent steps in the manufacturing process and also in melt fabrication.

The manufacturing process for the granules may optionally include sizing, such as screen granulation to mechanically force all the granules through a screen of selected mesh size which breaks up the oversize particles while maintaining the useful particle characteristics described herein. Some lump formation occurs during heat hardening and

-10-

5 fluorination. Such screen granulation is efficient  
in removing these lumps, which are detrimental in  
rotocasting operations.

10 These particles contain unstable end  
groups. The end groups found in the untreated  
polymer directly from polymerization depend on the  
initiator used and on the presence of pH and  
molecular weight modifiers. For example, if ammonium  
or potassium persulfate is employed as the initiator,  
the polymer end groups are essentially all carboxylic  
acid ( $-\text{CO}_2\text{H}$ ). The acid end groups are found in  
15 both monomeric or dimeric forms. If a pH modifier  
such as ammonium hydroxide is present, then a large  
portion of the carboxylic acid ends may be converted  
to amide ends ( $-\text{CONH}_2$ ). If a molecular weight  
modifier such as methanol is employed, then a portion  
20 of the ends may be carbinol ( $-\text{CH}_2\text{OH}$ ) as well as the  
more stable difluoromethyl ends ( $-\text{CF}_2\text{H}$ ). The  
presence of methanol can also lead to methyl ester  
ends ( $-\text{CO}_2\text{CH}_3$ ). Vinyl ends ( $-\text{CF}=\text{CF}_2$ ) are  
generally not a direct result of polymerization but  
25 are formed as a result of decarboxylation of the  
initially formed carboxylic acid ends. Acid fluoride  
ends ( $-\text{COF}$ ) generally result from air oxidation of  
the vinyl ends or the carbinol ends. All of the end  
groups described above (except  $-\text{CF}_2\text{H}$ ) are  
30 considered to be thermally and/or hydrolytically  
unstable. This is what is meant by the term  
"unstable end groups". They have a tendency to cause  
bubbles or voids upon melt fabrication. These voids  
can be detrimental to the physical or electrical  
35 properties of fabricated articles. It is desirable  
to have less than 80 of these unstable ends per  $10^6$   
carbon atoms in the polymer.

The unstable end groups described above may be reduced or eliminated by treatment of the polymer with fluorine. The fluorination may be carried out with a variety of fluorine radical generating compounds but preferably the polymer is contacted with fluorine gas. Since reactions with fluorine are very exothermic, it is preferred to dilute the fluorine with an inert gas such as nitrogen. The level of fluorine in the fluorine/inert gas mixture may be 1 to 50 volume % but is preferably 10-30%. Any reaction temperature between 0°C and the polymer melting point may be used but a temperature range between 130 and 200°C appears to be practical to permit reasonable reaction times (1 to 5 hours under fluorine). It is preferred to agitate the polymer to expose new surfaces continuously. The gas pressure during fluorination may range from atmospheric to 1 MPa. If an atmospheric pressure reactor is used, it is convenient to pass the fluorine/inert gas mixture through the reactor continuously. After exposure of the polymer for the desired length of time, the excess fluorine is purged from the sample, which is then cooled.

Most of the unstable end groups are converted to perfluoromethyl ( $-\text{CF}_3$ ) ends by the fluorine. The acid fluoride ends are the most resistant to fluorine but will react at sufficiently high temperature or with sufficient time.

The preferred copolymers should have a melting heat ratio greater than 1.2. By melting heat ratio is meant the ratio of the heat of melting on its first melting to the heat of melting recorded on a second melting. This is an indication that the particles have not been melted completely.

TEST PROCEDURESBUBBLE INDEX

- 5        The bubble index test referred to in the examples is performed as follows: A 15g sample of copolymer is weighed into a new clean aluminum pan which is about 50mm in diameter, 16mm deep and 0.08mm thick. The sample (with controls for comparison) is baked at  $50 \pm 5^\circ\text{C}$  above the melting point for 40 minutes in a high-temperature recirculating air oven. The baking time is defined as specimen exposure time between closing and opening the oven door. The oven air temperature is preset and recovers to set temperature within 5 to 10 minutes after sample addition. After cooling to room temperature, the polymer specimen is removed from the pan. The degree of bubble formation is observable qualitatively and is measured by the percentage increase in specific volume of the specimen relative to the bubble-free polymer. The Bubble Index is defined as:

$$\text{Bubble Index} = \left[ \left( \frac{(A - W) G}{A} \right) - 1 \right] 100$$

25    where:

- |    |   |   |   |
|----|---|---|---|
| 30 | G | = | Specific Gravity of bubble-free copolymer as determined by ASTM Method D-792. |
|    | A | = | Net weight of specimen in air.  |
| 35 | W | = | Net weight of specimen in water by displacement method.                       |

5 The entire exposed Bubble Index specimen is weighed in air and under water to the nearest 0.01 gram on an electronic balance. To obtain the net weight submerged in water, a stainless-steel wire harness with depth mark is suspended from a small ring stand on the balance and the tare weight of the harness is set to null in water before the specimen is added to the harness and submerged to the fixed depth. About 800 ml of demineralized water containing one drop of Triton\* X-100 or X-500 surfactant is used for submersion at room temperature. Specimens are observed under water to insure constant immersion depth and the absence of bubbles on the specimen surface.

#### ATTRITION FACTOR

20 Particle hardness is measured by a screening test as follows:  
Equipment:

Fritsch Pulverisette\*, Model 24-0217-000  
(Tekmar Company, Cincinnati, OH)

Sieve (USA Standard Testing Sieves)

- 25 - 51mm high x 203mm dia x 30 mesh for granules of D50 greater than 700 micrometers.
- 51mm high x 203mm dia x 80 mesh for granules of D50 less than 700 micrometers.

30 Pan and dome lid, 203mm dia.

19mm diameter stainless-steel balls (32g each)

#### Procedure:

35 Place 100.0 g of polymer ( $W_s$ ) onto the screen which has been placed on the preweighed pan ( $W_o$ ). Place the dome lid on top and position in the Fritsch Pulverisette(tm) apparatus. Preset amplitude to 1.5mm (amplitude setting of 3).

Attach the retaining straps to the lid and

\*denotes trade mark

5 tighten securely. Set the timer for 10 min and  
activate. At the end of 10 min remove the lid and  
screen, brushing polymer adhering to the inside of  
the bottom rim of the screen into the pan. Weigh the  
pan ( $W_1$ ). Place 12 of the stainless-steel balls on  
the screen and reassemble pan/screen/lid and place in  
10 the Pulverisette(tm). Set timer for 10 min and  
activate. After 10 min disassemble the screen again  
brushing polymer adhering to the inside of bottom rim  
into the pan. Weigh the pan and contents again  
( $W_2$ ). Calculate attrition factor as follows:

$$15 \quad \text{Attrition Factor} = \left[ \frac{W_2 - W_1}{W_s - W_1 - W_0} \right] 100$$

#### DETERMINATION OF SPHERE FACTOR

20 A small amount of sample is placed on a  
glass microscope slide, dispersed into a single layer  
by shaking slightly, and then photomicrographed. On  
a print, the largest and shortest diameters ( $a$  and  $b$ )  
of each particle are accurately measured to within  
 $\pm 5\%$  using more than 30 particles selected at random.

25 The sphere factor is calculated according to  
the method of U.S. Patent No. 3,911,072 as follows:

( $n$  = number of particles measured)

$$\text{Sphere Factor} = \frac{1}{n} \sum_{i=1}^n \frac{a_i}{b_i} \quad (i = 1, 2, 3, \dots, n)$$

#### END GROUP ANALYSIS

30 The end groups in a fluorocarbon polymer are  
determined from the infrared spectrum of compression  
molded films. This technique has been described in  
previous patents such as U.S. Patent 3,085,083.

35 The quantitative measurement of the number  
of end groups is obtained using the absorptivities  
measured on model compounds containing the end groups



5 of interest. The end groups of concern, the wavelengths involved, and the calibration factors determined from model compounds are shown below:

	Endgroup	Wavelength, micrometers	Calibration Factor (CF)
	-COF	5.31	406
	-CO <sub>2</sub> H(M)	5.52	335
10	-CO <sub>2</sub> H(D)	5.64	320
	-CO <sub>2</sub> CH <sub>3</sub>	5.57	368
	-CONH <sub>2</sub>	2.91	914
	-CF=CF <sub>2</sub>	5.57	635
	-CH <sub>2</sub> OH	2.75	2220

M = Monomeric, D = Dimeric

15 The calibration factor is a mathematical conversion to give end group values in terms of ends per 10<sup>6</sup> carbon atoms. The concentration of each type of end in a polymer film may generally be obtained from this equation:

$$20 \quad \text{End Groups per } 10^6 \text{ carbon atoms} = \frac{\text{absorbance} \times \text{CF}}{\text{film thickness}}$$

where film thickness is in millimeters ( $\pm 0.003\text{mm}$ ).

25 Some of the absorbance peaks may interfere with one another when -CO<sub>2</sub>H(D), -CO<sub>2</sub>H(M), and -CF=CF<sub>2</sub> ends are all present. Corrections have been developed for the absorbances of -CO<sub>2</sub>H(D) (hydrogen-bonded carboxylic acid dimer) and the  
30 -CF=CF<sub>2</sub> ends. These are as follows (where  $\mu$  is wavelength in micrometers):

$$35 \quad \frac{\text{absorbance } 5.46\mu - (0.3 \times \text{absorbance } 5.58\mu)}{0.91} = \text{corrected absorbance for } -\text{CO}_2\text{H(D)}$$

$$\frac{\text{absorbance } 5.57\mu - (0.3 \times \text{absorbance } 5.58\mu)}{0.91} = \text{corrected absorbance for } -\text{CF}=\text{CF}_2$$

5 The presence of  $-\text{CONH}_2$  or  $-\text{CO}_2\text{CH}_3$  may  
also interfere with the acid and  $-\text{CF}=\text{CF}_2$   
absorbances. Since these groups are generally the  
result of additives to polymerization their presence  
is generally predictable. A suspicion of  $-\text{CONH}_2$   
absorbance in the vicinity of 5.6 micrometers can be  
10 checked by searching for the auxiliary  $-\text{CONH}_2$  band  
at 2.91 micrometers.

The polymer films (0.25 to 0.30mm thick) are  
scanned on a Perkin-Elmer 283B spectrophotometer with  
a film of the same thickness, and known to contain  
15 none of the ends under analysis, in the instrument  
reference beam. The instrument is set up with a  
Response Time setting of 1, a Scan Time setting of 12  
minutes, Ordinate Expansion of 2, a Slit Program of  
7, and an Auto-Chek Gain control of 20%. The films  
20 are then scanned through the pertinent regions of the  
spectrum making sure that adequate base lines are  
established on each side of the pertinent absorbances.

The polymer films are generally compression  
molded at 270-350°C. The presence of certain salts,  
25 particularly alkali metal salts, may cause end group  
degradation within this temperature range. If these  
salts are present, the films should be molded at the  
lowest possible temperature.

#### HEXAFLUOROPROPYLENE (HFP) CONTENT DETERMINATION

30 The HFP content in the melt-processible  
TFE/HFP copolymers described herein is determined by  
measurement of the ratio of the infrared absorbance  
at 10.18 micrometers to the absorbance at 4.25  
micrometers. This ratio is referred to as the HFP

35 \*denotes trade mark

5 index or HFPI. Reference films of known HFP content, as determined by F19 NMR, are also run to calibrate the HFPI. The mole percent HFP present is equal to 2.1 times the HFPI. Compression-molded films approximately 0.10 - 0.11mm thick are scanned under a nitrogen atmosphere.

10 PERFLUOROPROPYL VINYL ETHER (PPVE) CONTENT DETERMINATION

15 The PPVE content in the melt-processible TFE/PPVE copolymers described herein is also determined by infrared spectroscopy. The ratio of absorbance at 10.07 micrometers to that at 4.25 micrometers is determined under a nitrogen atmosphere using films approximately 0.05 mm thick. The films are compression molded at 350°C, then immediately quenched in ice water. This absorbance ratio is then used to determine percent PPVE by means of a calibration curve established with reference films of known PPVE content. F19 NMR is used as the primary standard for calibrating the reference films.

20 AVERAGE PARTICLE SIZE

25 U.S. Patent 3,929,721 describes a dry-sieve analysis procedure. The "average particle size" is determined by a dry-sieving procedure in accordance with ASTM Procedure D-1457-B1a (12.3.3) modified as follows. The 203mm diameter sieve set is assembled in order, with the largest mesh opening on top. From the listing of U.S.A. Standard Testing Sieve sizes (ASTM E-11 Specification), four to eight adjacent sieves are selected with openings between the limits of 6 mesh and 200 mesh and which bracket the range into which the average particle size is expected to fall.

5 A 40 to 60g representative portion of the  
sample to be tested, preferably obtained using a  
sample splitter and weighed to the nearest 0.01g, is  
charged to the top screen. The screen set is shaken  
in a sieve shaker (typically a Ro-Tap\* shaker  
obtained from Fisher Scientific Co., Cat. No. 4-909)  
10 for about 10 minutes. After shaking, the net weight  
of material retained on each sieve is determined to  
the nearest 0.01g.

The weight average particle size is  
determined based on plotting the cumulative  
15 percentage retained vs. sieve opening on  
log-probability paper as described in ASTM method  
D-1921-63, or by equivalent computer interpolation of  
these data. The average particle size in micrometers  
is read from the plot at the 50th percentile (D50)  
20 abscissa of cumulative weight percentage retained.

#### DSC ANALYSIS

DSC analyses are carried out with a Du Pont  
Model 1090 Thermal Analyzer using a Model 910 DSC  
cell base and the Du Pont General Analysis Program,  
25 Version 1.0. The instrument is calibrated as  
recommended by the manufacturer, using a 10mg indium  
standard. Polymer sample size is 6 to 10 mg, crimped  
into an aluminum capsule. Different heating and  
cooling cycles are used depending upon the melting  
30 point of the sample. Samples are scanned twice  
across the melting endotherm at 10°C per minute from  
a temperature which is  $90 \pm 5^\circ\text{C}$  below to a  
temperature  $40 \pm 5^\circ\text{C}$  above the melting endotherm peak

\*denotes trade mark

35

temperature. Between the first and second scanning  
of the endotherm, the sample is cooled from the  
5 maximum to the minimum scan temperature at a rate of  
10°C/min. The "melting endotherm peak temperature"  
is defined as the peak temperature of the first  
melting endotherm. The heats of melting ( $H_1$  and  
10  $H_2$ ) are calculated from the first and second  
melting scans, respectively. The "melting heat  
ratio" ( $H_m$  ratio) is defined as  $H_1/H_2$ . The  
melting heats  $H_1$  and  $H_2$  are determined by  
instrumental integration using a base line from 80°C  
below to 30°C above the peak temperature. The "melt  
15 onset temperature" is determined graphically by  
plotting the derivative of the first melting scan  
using the Du Pont General Analysis Program, Version  
1.0. It is defined as the temperature where the  
expanded derivative curve first increases above the  
20 zero base line (on the low temperature edge of the  
melting curve) by 0.2 mW/min.

Example 1

A tetrafluoroethylene/hexafluoropropylene  
(TFE/HFP) copolymer, 7.6 mole % HFP, in aqueous  
25 dispersion form was obtained by polymerizing TFE and  
HFP in an aqueous medium according to the general  
procedure of U. S. Patent 4,380,618 using potassium  
and ammonium persulfate initiators and ammonium  
perfluorocaprylate surfactant. The copolymer was  
30 coagulated by using 1250 ml dispersion (26.4% solids)  
diluted with 500 ml of demineralized water in a  
3.5-liter stainless-steel beaker (152 mm in diameter)  
equipped with four equally spaced, rectangular  
baffles protruding 13 mm into the beaker. The  
35 agitator impeller had four 34mm x 17 mm x 3.2 mm  
thick blades welded onto a 17mm diameter hub at 35 to  
40° pitch from horizontal to pump upward when rotated

clockwise. Impeller diameter was 85mm. The contents were agitated at 900 rpm and 3.0 ml of 70 weight % nitric acid was then added to produce a thick gel. After 3 minutes, 160ml of Freon\* 113 was added to break the gel and granulate the polymer. Agitation was stopped 5 minutes later. The aqueous phase was poured off, 1000 ml of demineralized water was added, and the polymer agitated for 5 minutes at 500 rpm. The aqueous phase was again poured off and the polymer was dried in a 150°C air oven for 4 hours. This overall procedure was repeated three more times to obtain a total of 1500 g of polymer (melt viscosity  $6.2 \times 10^4$  poise at 372°C). This copolymer was screened on a 30-mesh sieve to remove fines and yield a product with a D50 of 1210 micrometers and a sphere factor of 1.33. About 1000g of this polymer was divided into eight essentially equal samples using a sample splitter. Seven of these samples were baked in an air oven at various conditions to harden the granules. The eighth sample was left unbaked as a control. The attrition factors measured on all eight samples are given below.

	Sample	<u>Baking Conditions</u>		<u>Attrition Factor</u>
		<u>Time, hrs</u>	<u>Temperature°C</u>	
30	1	2	222	35.5
	2	2	233	13.1
	3	4	233	4.7
	4	2	239	6.0
	5	4	239	2.2
	6	2	245	3.9
	7	4	245	1.8
	Unbaked control			92.3
35	*denotes trade mark			

5 All the temperatures for Samples 1 through 7 are between 25°C below the DSC melt onset temperature and the melt endotherm peak temperature.

10 Two samples of this polymer (125g each after screening to remove fines), one which had been baked at 239°C for four hours to harden the granules, and the second which was not baked, were fluorinated in a stainless-steel shaker tube for 4 hours at 160°C using a 25% fluorine in nitrogen atmosphere at 0.69 MPa gauge pressure. Total processing time was just over 5 hours. These samples were screened on a 30-mesh sieve to determine the amount of fines generated in the shaker-tube treatment with the following results:

	<u>Sample</u>	<u>Attrition Factor</u>	<u>% Fines Generated (through 30 mesh)</u>
20	Unbaked	92.3	6.1
	Baked at 239°C	2.2	0.5

DSC data were as follows:

	<u>Before Baking</u>	<u>After Baking</u>
25	Peak Temperature 262°C	263°C
	Melting Heat Ratio 1.45	1.56
	Melt Onset Temperature 248°C	244°C

30 The dried polymer had 440 unstable end groups per  $10^6$  carbon atoms. After fluorination no unstable end groups were detected.

#### Example 2

35 A TFE/HFP copolymer (5.9 mole % HFP) was polymerized at 3.1 MPa gauge pressure and 95°C with ammonium perfluorocaprylate dispersing

5 agent and ammonium persulfate initiator. The  
resulting dispersion (19.0% polymer) was coagulated  
similarly to that of Example 1. Per 100 parts of  
copolymer on a dry basis, 6 parts of 60 weight %  
nitric acid and 93 parts of Freon(tm) 113 were used.  
The polymer was washed several times with  
10 demineralized water to remove the nitric acid. The  
Freon(tm) was boiled off by a warm water (60°C) wash  
under slightly reduced pressure. The polymer was  
separated from the aqueous phase and dried/baked in a  
220°C circulating air oven for 8 hours. Analysis  
15 showed the presence of 448 unstable end groups per  
10<sup>6</sup> carbon atoms consisting of -COF, -CO<sub>2</sub>H(M),  
and -CO<sub>2</sub>H(D).

A 22.7-kg portion of the baked granules was  
treated with fluorine at 190°C for three hours while  
being tumbled in a vessel described as follows. The  
20 fluorination reactor was a 0.1 m<sup>3</sup> double-cone  
blender provided with gas inlet and vent connections  
and an electric heating mantle. The gas inlet dipped  
down into the particles and the vent pointed up into  
the vapor space. Both lines were fixed and remained  
25 stationary when the blender was rotated. The polymer  
granules were placed in the reactor which was then  
sealed and rotated at 5 rpm. The polymer was heated  
by both the electric mantle and a preheated air  
stream flowing through the reactor. When the polymer  
30 reached the desired temperature, the air flow was cut  
off and a vacuum was applied. The pressure was  
raised to atmospheric with a mixture of  
fluorine/nitrogen (25%/75% by volume) and this  
35 mixture was fed through the reactor continuously for  
three hours while maintaining the temperature with  
the electric mantle heater. The gas feed was then  
switched to 100% nitrogen until no fluorine was



-24-

5 detected in the off-gas using moistened starch-iodide paper. The resin was then cooled with cold air passed through the reactor. The reactor was then opened and the resin was collected. The granules had the following properties:

	Melt Viscosity	12.6 x 10 <sup>4</sup> poise at 372°C
10	Average Particle Size (D50)	1480 micrometers
	Attrition Factor	54.4
	Sphere Factor	1.16
15	Unstable Endgroups per 10 <sup>6</sup> Carbon Atoms	21
	DSC Melting Heat Ratio	1.60

20 The fluorinated granules were fed to a 32-mm diameter Waldron-Hartig\* extruder with a 20:1 L/D barrel and coated onto AWG #20 19/32 stranded copper conductor with an insulation thickness of 0.25mm. No electrical flaws were detected in the coating at either of two extruder temperature profiles. The  
25 coated wire had a dielectric strength of 69 kV/mm (ASTM D-149).

#### Example 3

30 An aqueous dispersion of tetrafluoroethylene (TFE) with 1.3 mole % perfluoropropyl vinyl ether (PPVE) copolymer was prepared in accordance with U.S. Patent 3,635,926. This dispersion, containing 26.9 weight % copolymer, was obtained by polymerizing the  
35 monomers using ammonium persulfate initiator, ammonium perfluorocaprylate surfactant and ethane chain-transfer agent in the presence of ammonium hydroxide pH modifier and Freon(tm) 113 as a water-immiscible phase.

\*denotes trade mark

-24-

5 The above TFE/PPVE copolymer dispersion was coagulated at 35°C by a method similar to that of Example 2. With agitation, 5.8 parts of 60 weight % nitric acid and 85.5 parts of Freon(tm) 113 per 100 parts by weight of copolymer (dry basis) were added.

10 The resulting granules were washed, with agitation, 3 times with 20-25°C demineralized water, followed by a wash heated to 60°C to remove the Freon(tm) 113, and by a final water wash at 20-40°C. The resulting polymer was separated from the wash water and dried at 180°C for 6 hours in a circulating air oven. The soft, granules were characterized as follows.

Average Particle Size (D50) = 360 micrometers

Attrition Factor = 81.8

Sphere Factor = 1.18

20 Melt Viscosity =  $3.9 \times 10^4$  poise at 372°C

PPVE Comonomer Content = 1.3 mole %

Melting Heat Ratio = 1.53

Melting Endotherm Peak Temperature = 311°C

Melt Onset Temperature = 287°C

25 Bubble Index = 26

The infrared scan showed 93 amide ends per  $10^6$  carbon atoms and a few vinyl and/or carboxylic acid ends per  $10^6$  carbon atoms.

30 The resin was heat hardened at about 285°C for three hours and the granules screened through a 20-mesh screen. They were characterized as follows.

Average Particle Size (D50) = 340 micrometers

Attrition Factor = 3.1

Melt Viscosity =  $7.9 \times 10^4$  poise at 372°C

35 PPVE Comonomer Content = 1.3 mole %

Melting Heat Ratio = 1.59

Melting Endotherm Peak Temperature = 311°C

Melt Onset Temperature = 289°C

Bubble Index = 66

5       The much reduced attrition factor shows a  
marked improvement in the hardness of the granules.  
Infrared analysis showed 88 amide ends and a few  
vinyl or carboxylic acid ends per  $10^6$  carbon atoms.

10       The resin was fluorinated using a high-  
pressure stainless-steel cylindrical batch reactor,  
equipped with gas and vacuum connections, electric  
heaters and shaker-type agitation. Polymer granules  
were charged and the vessel was sealed. A vacuum was  
applied followed by pressurization to 1 MPa gauge  
15       pressure with a mixture of fluorine/nitrogen (25%/75%  
by volume) at 190°C. The total processing time  
including start-up, venting and cool-down was just  
over 5 hours. The granules were heated in a  
circulating air oven for over an hour to remove  
traces of fluorine. Particle integrity was  
20       preserved. The granules were characterized as  
follows.

Average Particle Size (D50) = 285 micrometers

Attrition Factor = 6.3

Melt Viscosity =  $7.5 \times 10^4$  poise at 372°C

25       Melting Heat Ratio = 1.60

Melting Endotherm Peak Temperature = 311°C

Melt Onset Temperature = 291°C

Bubble Index = 15

30

35

5 Infrared analysis showed that fewer than 50  
unstable end groups per  $10^6$  carbon atoms were  
present after fluorination.

Example 4

10 By a procedure similar to that of Example 3,  
a heat-hardened resin was obtained. The granules  
were fluorinated as follows: An amount of polymer  
granules corresponding to about one-fourth of the  
reactor capacity was sealed inside the reactor of  
Example 2 and fluorinated for four hours at 185°C to  
189°C using a reactor rotation speed of 5 rpm. After  
15 fluorination, the granules were reduced in size by  
forcing them through a U.S. 30-mesh, 203-mm diameter  
sieve on a Fritsch Pulverisette(tm) shaker. Twelve  
stainless-steel balls 19mm in diameter were placed on  
the screen and vibrated until all the material,  
20 except for 3.6% of very hard particles which were  
discarded, had been forced through the screen.

The granulated resin was characterized as  
follows.

25 Average Particle Size (D50) = 337 micrometers  
Attrition Factor = 4.1  
Sphere Factor = 1.13  
Melt Viscosity =  $8.0 \times 10^4$  poise at 372°C  
PPVE Comonomer Content = 1.2 mole %  
Melting Heat Ratio = 1.56  
30 Melting Endotherm Peak Temperature = 311°C.

Melt Onset Temperature = 289°C

Infrared analysis indicated no detectable  
unstable end groups.

35

1248292

-28-

5       The Bubble Index on this sample was 11,  
compared to 45 for a non-heat-hardened, unfluorinated  
control sample.

10       A comparison was made of the rotolining  
performance of heat-hardened, fluorinated granules  
and unfluorinated control granules, using a 3-inch  
flanged pipe tee as a mold. A 647g quantity of the  
resin was placed inside the mold. The mold was then  
mounted in a fixture on one of the arms of the spider  
of a McNeil-Akron rotocasting machine of the type  
described in U.S. Patent No. 4,312,961. The machine  
15       was indexed to advance the arm into the oven. The  
mold was rotated by the fixture about mutually  
perpendicular axes to cause the resin to tumble and  
contact all interior surfaces of the mold. The  
major/minor axis speeds were 8/9 rpm respectively.  
20       The mold and its contents were heated for 15 minutes  
at 329°C before the temperature was raised to 352°C  
for the processing times shown below.

25       On completing the heating cycle, the spider  
arm indexed to a cooling station. While continuing  
its rotation, the part was cooled in sequence by an  
air stream for 5 minutes, by a water spray for 12  
minutes, and again by air for 2 minutes.

30       The rotocasting machine was then indexed to  
bring the finished part to the unloading station  
where it was removed. The lining of the finished  
part was inspected for bubbles or other porosity.  
The fluorinated resin of this invention gave a  
smoother surface than the control as shown in the  
table below.

35

-28-

1248292

-29-

	<u>Heat- Processing Conditions</u>	<u>Resin Type</u>	<u>Rotomolded Part Observations</u>
5	110 min, 352°C	Fluorinated	Bubble-free
	110 min, 352°C	Unfluori- nated	Many small lumps; bubbles in side neck
10	80 min, 352°C	Fluorinated	Bubble-free
	80 min, 352°C	Unfluori- nated	Many small lumps throughout part; many bubbles in middle of wall
15			
20			
25			
30			
35			

-29-

## We Claim:

- 5 1. A process for treating a melt-processible, substantially nonelastomeric tetrafluoroethylene copolymer prepared in an aqueous polymerization medium, which treatment comprises
- 10 A. coagulating from its aqueous polymerization medium a melt-processible tetrafluoroethylene copolymer comprising 80 to 99.5 mole % tetrafluoroethylene and 0.5 to 20 mole % of at least one copolymerizable comonomer, wherein
- 15 coagulation is carried out by causing the copolymer and medium to form a viscous gel by mechanical agitation or alternatively by addition of a chemical gelation agent, after which the resulting gel is broken into granules by addition of an essentially water-immiscible liquid accompanied by mechanical
- 20 agitation.
- B. separating the coagulated copolymer from the aqueous medium,
- C. removing liquid from the separated copolymer by drying,
- 25 D. partially sintering the dried copolymer at a temperature between 25°C below its differential scanning calorimeter melt onset temperature and its initial melt endotherm peak temperature until the attrition factor of the particles is less than 60, but before the copolymer becomes agglomerated,
- 30 E. subjecting the copolymer in D. to an atmosphere containing fluorine gas until the total number of unstable end groups is less than 80 per  $10^6$  carbon atoms,
- 35 F. followed by separating the copolymer from the atmosphere containing fluorine gas.

2. The process of Claim 1 wherein the chemical gelation agent for coagulation is at least one mineral acid.

5 3. The process of Claim 2 wherein the chemical gelation agent is nitric acid.

4. The process of any one of Claim 1, Claim 2 and Claim 3 wherein Steps D and E are conducted simultaneously.

10 5. Melt-processible, substantially nonelastomeric tetrafluoroethylene copolymer comprising 80-99.5 mole % tetrafluoroethylene and 0.5 to 20 mols % of at least one copolymerizable comonomer, which copolymer has

- 15 (a) a melt viscosity between  $0.1 \times 10^4$  and  $100 \times 10^4$  poise at  $372^\circ\text{C}$ ,
- (b) a substantially spherical particle shape and a sphere factor less than 1.5,
- (c) an attrition factor of less than 60,
- 20 (d) fewer than a total of 80 unstable end groups per  $10^6$  carbon atoms, said end groups comprising  $-\text{COOH}$ ,  $-\text{COF}$ ,  $-\text{CF}=\text{CF}_2$ ,  $-\text{CONH}_2$ ,  $-\text{CH}_2\text{OH}$ , or  $-\text{COOR}$ , where R is an alkyl group of 1-6 carbon atoms,
- 25 (e) an average particle size between 200 and 3000 micrometers.

6. The copolymer of Claim 5 which has a melting heat ratio greater than 1.20.

30 7. The copolymer of Claim 5 or Claim 6 wherein the melt viscosity is between  $0.5 \times 10^4$  and  $20 \times 10^4$  poise at  $372^\circ\text{C}$ , and the weight average particle size is between 200 and 500 micrometers.

35 8. The copolymer of Claim 5 or Claim 6 wherein the melt viscosity is between  $1 \times 10^4$  and  $100 \times 10^4$  poise at  $372^\circ\text{C}$ , and the weight average particle size is between 700 and 3000 micrometers.